

UNITED STATES PATENT AND TRADEMARK OFFICE  
**CERTIFICATE OF CORRECTION**

PATENT NO. : 6,831,029 B2  
APPLICATION NO. : 09/990750  
DATED : December 14, 2004  
INVENTOR(S) : Lisa C. Chacon et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Col. Line

12 39 Claim 62 reads "62. The glass of claim 23, wherein the glass has a liquidus viscosity greater than about 600,000 poises, a density less than about 2.40 grams/cm<sup>3</sup>, and a strain point greater than about 850°C."


Claim 62 should read --62. The glass of claim 23, wherein the glass has a liquidus viscosity greater than about 600,000 poises, a density less than about 2.40 grams/cm<sup>3</sup>, and a strain point greater than about 650°C--

13 4 Claim 69 reads "69. The glass of claim 23, wherein the glass has a liquidus viscosity greater than about 800,000 poises, a density less than about 2.40 gram/cm<sup>3</sup>, and exhibits a weight loss of less than 0.5 mg/cm<sup>2</sup> after immersion in a solution oil 1 part 50 wt.% HF and 10 parts 40 wt.% NH<sub>4</sub>F for 5 minutes at 30°C."

Claim 69 should read --69. The glass of claim 23, wherein the glass has a liquidus viscosity greater than about 800,000 poises, a density less than about 2.40 gram/cm<sup>3</sup>, and exhibits a weight loss of less than 0.5 mg/cm<sup>2</sup> after immersion in a solution of 1 part 50 wt.% HF and 10 parts 40 wt.% NH<sub>4</sub>F for 5 minutes at 30°C.--

Signed and Sealed this

Twentieth Day of November, 2007



JON W. DUDAS

*Director of the United States Patent and Trademark Office*